



Cellular Confinement Systems - Geocell

# EGA-P



12626 North Houston Rosslyn Rd.  
Houston, TX USA 77086  
Phone: (281) 820-5493  
Fax: (281) 820-5499  
www.geoproducts.org

The EnviroGrid Paver creates a porous stable surface that will help you comply with new stormwater management regulations. The use of the EnviroGrid Paver reduces runoff volumes and helps protect and conserve natural areas. Section and cell size will change as each section is expanded to the required dimension. Section length can be increased or decreased by adding or subtracting cells at no additional charge.

Material Properties	Test Method	Unit	Test Value
Polymer Density	ASTM D 1505	g/cm <sup>3</sup> (lb/ft <sup>3</sup> )	0.935-0.965 (58.4-60.2)
Environmental Stress Crack Resistance	ASTM D 1693	hours	6,000
Carbon Black Content	ASTM D 1603	% by weight	1.5% minimum

Standard sections are manufactured from 58 strips of HDPE, resulting in a section length of 29 cells and 10 cells wide. Each strip is the appropriate width and 82 inches (2.08m) in length. Weld spacing is 8.0 in ± .12 in (203 ± 3mm).

Physical Properties	Unit	Test Value			
Nominal - Expanded Cell Size (width x length)	mm (in)	146 (5.75) x 127 (5) 92.9			
Nominal - Expanded Cell Area	cm <sup>2</sup> (in <sup>2</sup> )	(14.4)			
Nominal - Expanded Section (width x length)	m (ft)	1.46 (4.8) x 3.68 (12.08)			
Nominal - Expanded Section Area	m <sup>2</sup> (ft <sup>2</sup> )	5.4 (58)			
Cell Depth	mm (in)	50 (2.0)	75 (3.0)	100 (4.0)	125 (5.0)
Seam Peel Strength	N (lbf)	710 (160)	1065(240)	1420 (320)	1775 (400)
Seam Hang Sterength	A 102mm (4.0in) weld joint supporting a load of 72.5 kg (160 lbs) for 30 days minimum or a 102mm (4.0in) weld joint supporting a load of 72.5 kg (160 lbs) for 7 days minimum while undergoing temperature change from 23°C (74°F) to 54°C (130°F) on a 1 hour cycle.				

